


ADDΣZIV

Innovation in Every Bond



T101 Classic

PRODUCT BENEFITS



Strong and
durable bond



Resistance to
shrinkage



Easy to mix
and apply



Addeziv T101 Classic

Addeziv T101 Classic is a polymer-modified, grey cement-based tile adhesive specifically designed for interior floor & wall applications.

Area of Application

Addeziv T101 Classic is compatible with porous tiles, such as ceramic, porcelain and small format natural stones for dry areas of interior floor and wall applications. Can be used up to 12mm bed thickness.

Substrates

Brick Masonry • Cement Plaster • Cement Concrete • Cement Screed
Cement Terrazzo • Cement Mortar Beds

Product Benefits

Single component, just add water • Interior floor & wall application • Easy to mix and apply
Strong & durable bond to various substrates • Resistance to shrinkage
Complies with IS 15477:2019 Type 1T • Conforms to EN 12004 C1T



HOW TO USE



Surface Preparation:

Surface should be clean from any loose particles including dust, oil/grease etc. For best results use it on damp surface.



Application and Spreading:

- Apply the mix uniformly using trowel with thickness of 4-6 mm and then comb with notch trowel.
- Tiles should be placed within 10-15 minutes after applying the mix.
- Addeziv T101 Classic mix should be applied on the back of tiles before placement.
- Fix the tiles with sliding motion and hammer gently with a soft mallet.



Blending of Addeziv T101 Classic

- Gradually mix it with potable water (5-6 Ltr) to prepare workable and lumps free paste.
- Waiting Time: Wait for 5-10 minutes after preparing the paste.



Cleaning of Tile:

Excessive adhesive should be cleaned from the joints and surface of tiles.



Grouting:

- Grouting should be carried out only after 24 hours of tile placement.
- Grout with Addeziv TG21 cementitious grout.
- Use Addeziv EG51 epoxy grout for stain free grouting.

Technical Information

Test specifications requirement As per IS 15477:2019			
Test	Test Methods	Specification	Result
Physical Appearance	Visual	Grey Cementitious Powder	Grey Cementitious Powder
Bulk Density	Internal	1.50 - 1.90 gm/ml	1.73 gm/ml
Flow Point	Internal	165 - 210 mm	180 mm
Open Time	IS-15477 -2019	>5 minutes.	>5 minutes
Pot Life	Internal	>30 minutes	80 - 120 minutes
Spreadability	Internal	Spread Easily with Good Notchability	Spread Easily with Good Notchability
Adjustability	IS 15477 : 2019	>5 minutes	>5 minutes
Slip Resistance	IS 15477 : 2019	<0.5 mm	0.25 - 0.35 mm
Tensile Adhesion	IS 15477:2019 Dry Condition	≥0.5 N/mm ²	0.55 - 0.70 N/mm ²
Shear Adhesion	IS 15477:2019 Dry Condition	≥1.0 N/mm ²	1.05 - 1.2 N/mm ²

Caution: It contains Portland cement, avoid contact with eyes. In case of eye contact use plenty of water and visit certified doctor.

Note: - Actual performance and strength will depend on site conditions, method of preparation and application.

ADDEZIV
Innovation in Every Bond

Real One Adhesive Pvt Ltd : 405, 4th Floor, Geetansh Class of Pearl,
SL Marg, Durgapura, Tonk Road, Jaipur, Rajasthan, 302018
✉ info@addeziv.com ☎ 0141 6657596 🌐 www.addeziv.com

Disclaimer: The Company provides guarantee against defective material, but the application and usage of products are made without guarantee since the application conditions are not in its control. All products are tested under the recommended conditions of temperature 27 ± 2°C and humidity 65 ± 5 %. Company recommends to verify the suitability of the product for intended use with the latest version of data sheet. The Company may modify product data sheet without any prior notice. All technical characteristics are listed for guidance only and Addeziv technical team may be contacted for more information.

Coverage

- 50-55 ft² per 20 kg bag using a square notched trowel for fine thin bed fixing.
- Coverage may vary depending on trowel notch size, size of the tile, substrate type and site conditions.

Storage Life

- 12 months from the date of manufacturing, if placed in cool and dry area.

Packaging : 20 kg bag

Important Notes

- Do not add excess water than recommended
- Always add powder to water
- Protect from direct rain and foot/traffic movement for at least 24 hours

